

PATENT



Docket No. 979-067

IFW

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant(s) : TBA
Serial No. : 10/826,146
Filed : April 15, 2004
For : CABLE WITH CREVICE CORROSION PROTECTION

CERTIFICATE OF MAILING (37 C.F.R. 1.8a)

Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

Sir:

I hereby certify that the attached Communication, Certified Copy of Priority Document, and Return Postcard along with any paper(s) referred to as being attached or enclosed and this Certificate of Mailing are being deposited with the United States Postal Service on the date shown below with sufficient postage as first-class mail in an envelope addressed to the: Commissioner for Patents, Alexandria, V.A.. 22313.

Respectfully submitted,


SOFER & HAROUN, L.L.P.

By: *Sandra Cirillo*
Sandria Cirillo

Date: 6/15/04

Mailing Address:

SOFER & HAROUN, L.L.P.
317 Madison Avenue, Suite 910
New York, New York 10017
Tel:(212)697-2800
Fax:(212)697-3004



Docket No.: 979-067

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

-----X
In re Application of

TBA

Serial No.: 10/826,146

Filed: April 15, 2004

For: CABLE WITH CREVICE CORROSION PROTECTION:
-----X

COMMUNICATION

Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

SIR:

In connection with the above-identified matter, enclosed please find a Certified Copy of Priority Document.

In the event that any fees or charges are deemed necessary in connection with the application at the present time, the same may be charged to Deposit Account No. 19-2825, Order No.: 979-067.

Respectfully submitted,

SOFER & HAROUN, LLP

By 

Joseph Sofer, Esq.

Reg. No. 34,438

317 Madison Avenue, Suite 910

New York, New York 10017

(212) 697-2800

Dated: June 15, 2004



BEST AVAILABLE COPY

KONGERIKET NORGE
The Kingdom of Norway

Bekreftelse på patentsøknad nr
Certification of patent application no

▼
20032028

► Det bekreftes herved at vedheftede dokument er nøyaktig utskrift/kopi av ovennevnte søknad, som opprinnelig inngitt 2003.05.06

► *It is hereby certified that the annexed document is a true copy of the above-mentioned application, as originally filed on 2003.05.06*

2004.04.20

Line Reum

Line Reum
Saksbehandler



PATENTSTYRET®
Styret for det industrielle rettsvern



PATENTSTYRET
Styret for det industrielle rettsvern

ADRESSE

Postboks 8160 Dep.
Københavngaten 10
0033 Oslo

TELEFON

22 38 73 00

TELEFAKS

22 38 73 01

BANKGIRO

8276.01.00192

FORETAKSNUMMER

971526157

Søknad om patent

Søkers/fullmektigens referanse
(angis hvis ønsket):

84635-SS

Skal utfylles av Patentstyret

Behandlende medlem *MP*
Int. Cl⁸ *D 07 B*

Oppfinnelsens
benevnelse:

Mot sprekkorrosjon beskyttet kabel

Alm.tilgj. - 8 NOV. 2004

Hvis søknaden er
en internasjonal søknad
som videreføres etter
patentlovens § 31:

Den internasjonale søknads nummer

Den internasjonale søknads inngivelsesdag

Søker:

Navn, bopel og adresse.
(Hvis patent søkes av flere:
opplysning om hvem som skal
være bemyndighet til å motta
meddelelser fra Patentstyret på
vegne av søkerne).

(Fortsett om nødvendig på neste side)

Nexans
16 rue de Monceau
FR-75008 Paris

☐ Søker er en enkeltperson eller en småbedrift, eller flere slike i fellesskap med fast ansatte som til-
sammen utfører 20 årsverk eller mindre (på søknadstidspunktet). Det er søkers ansvar å krysse av her
for å oppnå laveste satser for søknadsavgift. NB! se også utfyllende forklaring på siste side.

Oppfinner:

Navn og (privat-) adresse

(Fortsett om nødvendig på neste side)

Stian Karlsen
Bratnerenga 11
1785 Halden

Oppfinneren er ansatt i søkerfirmaet

Fullmektig:

Tandbergs Patentkontor AS

Hvis søknad tidligere
er inngitt i eller
utenfor riket:

(Fortsett om nødvendig på neste side)

Prioritet kreves fra dato *Ingen* sted nr.
Prioritet kreves fra dato sted nr.
Prioritet kreves fra dato sted nr.

Hvis avdelt søknad:

Den opprinnelige søknads nr.: og deres inngivelsesdag

Hvis utskilt søknad:

Den opprinnelige søknads nr.: begjært inngivelsesdag

Deponert kultur av
mikroorganisme:

☐ Søknaden omfatter kultur av mikroorganisme. Oppgi også deponeringssted og nr.

Utlevering av prøve av
kulturen:

☐ Prøve av den deponerte kultur av mikroorganisme skal bare utleveres til en særlig sakkyndig,
jfr. patentlovens § 22 åttende ledd og patentforskriftenes § 38 første ledd

Angivelse av tegnings-
figur som ønskes
publisert sammen med
sammendraget

Fig. nr. *1*

03-05-06 20032028

CABLE WITH CREVICE CORROSION PROTECTION

The invention relates to a cable with crevice corrosion protection, specially a subsea line or umbilical.

In narrow crevices filled with corrosive fluid, there is a risk for a type
5 of local corrosion, called crevice corrosion, on passive metals. Passive metal means here metal, which is not immune to the corrosive fluid that it is exposed to, but protected by a strong oxide layer produced by the alloy elements. This oxide layer produces a passive film on the metal that may be broken due to the sour conditions that comes into being in crevices. An
10 example of such passive metal is super duplex steel.

Crevice corrosion appears when the following conditions are present: a crevice with a critical geometry, an oxidation agent, normally oxygen, and eventually chloride ions, which will reduce the initiation time and increase the corrosion rate.

15 The exchange of ions in the corrosive fluid between the volume inside and outside of a crevice will be limited, thereby causing reduction of oxygen and increasing of chloride concentration in the crevice. The smaller the crevice opening and the longer the crevice length, the more the exchange of ions will be prevented. In a crevice with a critical geometry, this
20 mechanism will cause corrosion.

Subsea lines or umbilicals comprise a number of fluid/gas conducting steel tubes and other elongated elements like electrical conductors and cables enclosed within a common outer cover.

In subsea umbilicals, there are crevices between the elements. One
25 or more of the elements in the umbilical might be hydraulic or injection tubes of a passive metal, most commonly super duplex steel. Seawater is a corrosive fluid that might fill the space and crevices between the elements.

In seawater the risk for crevice corrosion is increasing with increasing temperature. Crevice corrosion on super duplex steel is believed to be a
30 potential problem in seawater at temperatures above 25 degree C.

The challenge has been to achieve corrosion protection of the super duplex steel tubes at temperatures above 25 degree C.

Most prior art solutions include an outer complete extruded polymer sheath over the concerned tubes. Such plastic coating minimizes the risk for
5 crevice corrosion, by avoiding direct seawater access to the metal tubes.

But this arrangement is very dependent on the quality of the plastic sheath surrounding the tube. If there are openings in the plastic sheath, due to damage, these openings are of uncontrolled dimensions not allowing free water passage, so that crevice corrosion may still happen under the sheath,
10 close to the openings.

The invention solves this technical problem and for that it relates to a cable comprising at least two elongated elements chosen from a group consisting of steel tubes, optical fiber cables, electrical cables, and combinations thereof, arranged side by side within a common outer cover
15 along the length of the line and where at least one of the elongated elements has a passive metal outer surface, said outer cover allowing entrance of corrosive agent to the interstices between elements, characterized in that at least one of the elements with passive metal outer surface is provided with an outer layer formed of a material with open structure for water passage and
20 having controlled thickness.

This outer layer will ease the transport of ions in the corrosive agent around the passive metal and thereby reduce local depletion of oxygen and local concentration of chloride ions. Thus crevice corrosion may be prevented.

25 In a first embodiment of the invention, said outer layer is of fibrous material.

Preferably, said outer layer is of a woven material.

The fibrous material of said outer layer can be chosen among synthetic fibers such as polyester, polyamide or combination of these
30 materials, - or natural fibers such as cotton or other plant fibers or wool.

In a second embodiment of the invention, said outer layer is of a non-fibrous material with evenly distributed voids.

Said layer can consist of a tape wound around the surface or of a tape arranged longitudinally along the surface of the said element with passive metal outer surface.

Preferably, said layer has a thickness greater than 0.1 mm.

5 The invention relates to a subsea line like specified here above, corrosive agent being seawater.

A preferred embodiment of the invention is described with reference to drawings, which are not limitative.

10 Figure 1 is a section view of a subsea line or umbilical conforming to the invention.

Figure 2 shows a detail of a subsea line or umbilical conforming to the invention, in section view.

Figure 1 shows an embodiment of a static subsea steel tube umbilical having a core 1 forming by an inner stainless steel tube, for example super duplex steel tube, and which may be a fluid pipe. This core 1 provides the centre element of the line when stranding other elongated elements such as hydraulic tubes 2 made of stainless steel, for example super duplex steel tube, optical fiber cables 3 and/or electrical cables 4 over the core 1.

20 Over the layer of tubes 2 and cables 3, 4, there are provided an outer protection layer 5 consisting of wound PP yarn or an extruded PE sheath. The line may include filler elements 6 limiting free space between longitudinal elements 2, 3, 4 of the line. In the embodiment of the invention shown in figure 1, the stainless steel core 1 has an outer diameter of 66 mm.

25 In this arrangement, the core 1 and the hydraulic tubes 2 are made of said passive metal, but more generally, all metal tubes in the line, like outer sheaths of optical fiber cable 3 and electrical cables 4 can be of passive metal like stainless steel.

30 Conforming to the invention, these elements with passive metal outer surface are provided with outer layer formed of a material with open structure for water passage and having controlled thickness. More precisely, the core 1

is provided with an outer layer 1A and the hydraulic tubes 2 with outer layers 2A creating space around the passive metal.

These outer layers 1A, 2A can be of a woven or no woven material of synthetic or natural fiber such as for example polyester, polyamide or
5 combination of these materials, - or cotton or other plant fibers or wool.

These outer layers 1A, 2A can be of a non fibrous material with evenly distributed voids.

The figure 2 shows in detail such layer 1A around the core 1 formed by a woven material.

10 This layer can consist of a tape wound around the surface of the said element or of a tape arranged longitudinally along the surface of the said element with passive metal outer surface.

These layers create small openings between the tube of passive metal and the adjacent element. These small openings will ease the transport
15 of ions in the seawater around the tube and thereby reduce local depletion of oxygen and local concentration of chloride ions.


In order to obtain the protection against crevice corrosion, the said layer must have an open structure for water passage and having controlled thickness. The thickness must be large enough to open up the crevice and
20 obtain tensile strength during production and wear strength during service. The structure must be such that the water can pass between the metal and the adjacent element.

Preferably, said layer has a thickness of at least 0.1 mm.

Grease or dirt might cover the openings in the layer 1A, 2A and
25 prevent water penetration. This should however easily be avoided by proper care during umbilical production.

In the here above described embodiment, the outer layer 1A, 2A is provided around the element with passive metal outer surface. More generally, it can be provided between the element with passive metal outer
30 surface and the adjacent element, around element with passive metal outer surface and/or around adjacent element.

In the here above described embodiment, the cable is a subsea line or umbilical but the invention can be applied in all types of cable comprising at least two elongated elements chosen from a group consisting of tubes, electrical cables, optical fibber cables and combinations thereof, arranged
5 side by side within a common outer cover along the length of the line and where at least one of the elongated elements has a passive metal outer surface, said outer cover allowing entrance of corrosive agent to the interstices between elements, an outer layer being provided between said element with passive metal outer surface and an adjacent element.
10 Examples of such cables are cables exposed to sour and corrosive water like cables in watering earth like bog.



CLAIMS

1. Cable comprising at least two elongated elements chosen from a group consisting of steel tubes (1, 2), optical fibber cables (3),
 5 electrical cables (4), and combinations thereof, arranged side by side within a common outer cover (5) along the length of the line and where at least one of the elongated elements (1, 2) has a passive metal outer surface, said outer cover (6) allowing entrance of corrosive agent to the interstices between elements, characterized in that at least one of the elements (1,2) with passive
 10 metal outer surface is provided with an outer layer (1A, 2A) formed of a material with open structure for water passage and having controlled thickness.

2. Cable according to claim 1, characterized in that said outer layer is of fibrous material.

15 3. Cable according to claim 2, characterized in that said outer layer (1A, 2A) is of woven material.

4. Cable according to claim 2 or 3, characterized in that the fibrous material of the outer layer (1A, 2A) is chosen among synthetic fibbers such as polyester, polyamide or combination of these materials.

20 5. Cable according to claim 2 or 3, characterized in that the fibrous material of the outer layer (1A, 2A) is chosen among natural fibbers such as cotton or other plant fibbers or wool.


6. Cable according to claim 1, characterized in that said outer layer is of a non-fibrous material with evenly distributed voids.

25 7. Cable according to one preceding claim, characterized in that said outer layer consists of a tape wound around the surface of the said element with passive metal outer surface.

8. Cable according to one preceding claim, characterized in that said outer layer consists of a tape arranged longitudinally along the surface
 30 of the said element with passive metal outer surface.

9. Cable according to one preceding claim, characterized in that said outer layer has a minimum thickness of 0.1 mm.

10. Subsea line according to one preceding claim, corrosive agent being seawater.



ABSTRACT

The invention relates to a cable comprising at least two elongated elements chosen from a group consisting of steel tubes (1, 2), optical fiber cables (3), electrical cables (4), and combinations thereof, arranged side by side within a common outer cover (5) along the length of the line and where at least one of the elongated elements (1, 2) has a passive metal outer surface, said outer cover (5) allowing entrance of corrosive agent to the interstices between elements, characterized in that at least one of the elements (1,2) with passive metal outer surface is provided with an outer layer (1A, 2A) formed of a material with open structure for water passage and having controlled thickness.

Figure à publier : 1.



